

COATING SYSTEM SPECIFICATIONS (Rev: 10/07)

Polymer thicknesses exclude primer and sand. Millages shown are minimums and are for use only as guidelines. Requirements will vary depending upon temperature, substrate profile, service conditions and other factors.

Iso-Flex 750 U Coating System

	<u>MVT</u>	<u>HVT</u>
Iso-Flex Primer 750		
Iso-Flex 750 Base Coat	25 mils	25 mils
Iso-Flex 750 Top Coat		15 mils
16-30 Mesh Sand		6-8 lbs/100 ft ²
Iso-Flex 750 Top Coat	15 mils	15 mils
16-30 Mesh Sand	6-8 lbs/100 ft ²	6-8 lbs/100 ft ²
Total Polymer Thickness	40 mils	55 mils

Iso-Flex 750U-HL Coating System

	<u>MVT</u>	<u>HVT</u>
Iso-Flex Primer 750		
Iso-Flex 750 Base Coat	25 mils	25 mils
Iso-Flex 750 IC	10 mils	15 mils
16-30 Mesh Sand	½ lb/ft ²	¾ lb/ft ²
Iso-Flex 750 Top Coat	12 mils	12 mils
Total Polymer Thickness	47 mils	52 mils

Iso-Flex 750EU Coating System

	<u>MVT</u>	<u>HVT</u>
Iso-Flex Primer 750 or Iso-Flex Epoxy SF Primer		
Iso-Flex 750 Base Coat	25 mils	25 mils
Iso-Flex Epoxy 200 Wear Coat	10 mils	20 mils
16-30 Mesh Sand	½ lb/ft ²	1 lb/ft ²
Iso-Flex Epoxy 200 Lock Coat	16 mils	16 mils
Total Polymer Thickness	51 mils	61 mils

Iso-Flex 760 U Low Odor Two Coat System

	<u>MVT</u>	<u>HVT</u>
Iso-Flex Primer (Epoxy SF, #20 Low Odor or 757)		
Iso-Flex 750 Base Coat	25 mils	25 mils
Iso-Flex 760 LC Wear Course	15 mils	25 mils
12-20 Mesh Sand	10-12 lbs/100 sq.ft	25-30 lbs/100 sq.ft
Total Polymer Thickness	40 mils	50 mils

SYSTEM SPECIFICATIONS page 2 of 3

Iso-Flex 760 U Low Odor Coating System

	<u>MVT</u>	<u>HVT</u>
Iso-Flex Primer (Epoxy SF, #20 Low Odor or 757)		
Iso-Flex 750 Base Coat	25 mils	25 mils
Iso-Flex 760 Lock Coat		15 mils
16-30 Mesh Sand		6-8 lbs/100 ft ²
Iso-Flex 760 Lock Coat	15 mils	15 mils
16-30 Mesh Sand	6-8 lbs/100 ft ²	6-8 lbs/100 ft ²
Total Polymer Thickness	40 mils	55 mils

Iso-Flex 760 U-HL Low Odor Coating System

	<u>MVT</u>	<u>HVT</u>
Iso-Flex Primer (Epoxy SF, #20 Low Odor or 757)		
Iso-Flex 750 Base Coat	25 mils	25 mils
Iso-Flex 760 IC	10 mils	15 mils
16-30 Mesh Sand	½ lb/ft ²	¾ lb/ft ²
Iso-Flex 760 Lock Coat	14 mils	14 mils
Total Polymer Thickness	49 mils	54 mils

Iso-Flex 760 U VC Coating System

	<u>MVT</u>	<u>HVT</u>
Iso-Flex Primer (Epoxy SF, #20 Low Odor or 757)		
Iso-Flex 760 ZV Base Coat	20 mils	20 mils
Iso-Flex 760 Lock Coat		15 mils
16-30 Mesh Sand		6-8 lbs/100 ft ²
Iso-Flex 760 Lock Coat	15 mils	15 mils
16-30 Mesh Sand	6-8 lbs/100 ft ²	6-8 lbs/100 ft ²
Total Polymer Thickness	35 mils	50 mils

Iso-Flex 760 U-HL VC Coating System

	<u>MVT</u>	<u>HVT</u>
Iso-Flex Primer (Epoxy SF, #20 Low Odor or 757)		
Iso-Flex 760 ZV Base Coat	20 mils	20 mils
Iso-Flex 760 Lock Coat	10 mils	15 mils
16-30 Mesh Sand	1/2 lbs/ft ²	3/4 lbs/ft ²
Iso-Flex 760 Lock Coat	12 mils	12 mils
Total Polymer Thickness	35 mils	50 mils

SYSTEM SPECIFICATIONS page 3 of 3

Iso Flex 780/750 U Coating System

	<u>MVT</u>	<u>HVT</u>
Iso-Flex Primer 750		
Iso-Flex 780 Base Coat	20 mils	20 mils
Iso-Flex 750 Top Coat		15 mils
16-30 Mesh Sand		6-8 lbs/100 ft ²
Iso-Flex 750 Top Coat	15 mils	15 mils
16-30 Mesh Sand	6-8 lbs/100 ft ²	6-8 lbs/100 ft ²
Total Polymer Thickness	35 mils	50 mils

Iso-Flex 780/750 U-HL Coating System

	<u>MVT</u>	<u>HVT</u>
Iso-Flex Primer 750		
Iso-Flex 780 Base Coat	20 mils	20 mils
Iso-Flex 780 IC	10 mils	15 mils
16-30 Mesh Sand	½ lb/ft ²	¾ lb/ft ²
Iso-Flex 750 Top Coat	12 mils	12 mils
Total Polymer Thickness	42 mils	47 mils